

Product: Genflam® XLOH-S
Gendon Code: 2369 (Black)
2382 (White)
2477 (Red)



Revision Date: Dec 16, 2019

Genflam® XLOH-S fast peroxide curing thermoset flame retardant low smoke zero halogen compound was designed to provide the wire and cable field with a quick curing jacketing compound that gives excellent physical properties while processing easily. This polyolefin product passes MIL 24643B and MIL 24640B military shipboard cable requirements.

Key Features:

- High flame retardancy
- Good processibility
- Uses no heavy metals or halogenated ingredients

Physical Properties:

Density:	1.52 g/cm ³	Durometer:	96 Shore A
Tensile:	1700 psi (typical)	Low Temp. Brittle Point:	-35°C
Elongation:	200% (typical)	Deformation, 2000g:	1.5%@121°C
Tear:	50 lbf/in (typical)		

Combustion Properties:

Limited Oxygen Index (LOI):	40%
Acid Gas:	0.2%

Heat Aging:

	<u>7d@136°C</u>
Tensile Retention	168%
Elongation Retention	65%
Hot Creep @ 200°C	0.15%
Hot Set @ 200°C	0%

Fluid Resistance:

	<u>IRM902 - 18h@121°C</u>	<u>Diesel - 24h@100°C</u>	<u>IPA - 24h@RT</u>
Tensile Retention	93%	53%	102%
Elongation Retention	65%	105%	95%

Weathering:

	<u>720 Hours under QUV Testing</u>
Tensile Retention	145%
Elongation Retention	86%

Suggested Running Conditions:

Extruder L/D:	15:1 or 20:1	Comp. Ratio:	1.25:1	Screen Pack:	20 Mesh or none
Screw Type:	Single Flight metering, without mixing section				
Feed Zone:	190°F	Center Zone:	190-200°F	Head/Die:	220°F
Conductor Pre-heat:	150°F (recommended)				

Processing Techniques: Gendon's XLOH-S Zero Halogen compound is designed to process easily and maintain low scrap rates.
